

IMPACT™ Properties		ASTM Test Method	Typical Values		
Grade/Instrumented Impact Strength (LB)			19	24	34
Yield (sq.in. per pound)			50000	40000	30000
Haze (%)		D 1003-95	3.1	3.3	3.7
Gloss (%)		D 2457-90	87	87	87
Clarity (%)		D 1746-92	86	85	81
Coefficient of Friction (film-to-film, kinetic)		D 1894-95	0.22	0.22	0.23
Water Vapor Transmission Rate (gms/100sq. In./24 hrs.)		F 1249-90	1.3	1.1	0.9
Oxygen Transmission Rate (cc/m ² / 24 hrs. @ 73 °F., 1 atm)		D 3985-95	8548	6726	4941
Tear Propagation (gms)	LD* / TD**	D 1938	3.8 / 4.9	5.3 / 6.0	8.5 / 9.2
Elongation at Break (%)	LD* / TD**	D 882-95	95 / 30	110 / 135	125 / 140
Minimum Use Temperature			-60°F		
Maximum Storage Temperature			90°F		
			LD*		TD**
Tensile Strength (psi)		D 882-95	17500		19000
Modulus of Elasticity (psi @ 73 °F)		D 882-95	60000		65000
Free Shrink (%) @200 °F		D 2732-83	14		20
@220 °F			22		33
@240 °F			57		60
@260 °F			77		77
Shrink Tension (psi) @200 °F		D 2838-95	350		500
@220 °F			400		570
@240 °F			440		600
@260 °F			440		535
@280 °F			420		450
* Longitudinal Direction ** Transverse Direction					
This information represents our best judgement based on the work done, but the Company assumes no liability whatsoever in connection with the use of information or findings contained herein. Impact™ shrink film complies with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, for the packaging of all foods, with the exception of high alcoholic, at temperatures of 65 °C and below.					